**LAPEROS® LCP**Grade Catalog

**Liquid Crystal Polymer (LCP)** 

## **LAPEROS®**

GA130

VF2201/BK210P

Standard, High flow, for SMT

POLYPLASTICS CO., LTD.

## General Properties of GA130

table1-1 General Properties (ISO)

table1-1 Gener	rai Properties	(150)	
ltem	Unit	Test Method	Standard, High flow, for SMT
			GA130
			GF Reinforced
Color			VF2201/BK210P
ISO(JIS)quality-of-the-material display:		ISO11469 (JIS K6999)	>LCP-GF30<
Density	g/cm <sup>3</sup>	ISO 1183	1.61
Water absorption (23°C,24hrs,1mmt)	%	ISO 62	0.02
Tensile strength	MPa	ASTM D638	150
Tensile elongation	%	ASTM D638	1.6
Flexural strength	MPa	ISO 178	200
Flexural modulus	MPa	ISO 178	15,000
Flexural strain	%	ISO 178	1.8
Charpy notched impact strength (23 $^{\circ}$ C)	kJ/m²	ISO 179/1eA	20
Temperature of deflection under load (1.8MPa)	$^{\circ}$	ISO 75-1,2	280
Temperature of deflection under load (0.45MPa)	$^{\circ}$ C	ISO 75-1,2	300
Electric strength (1mmt)	kV/mm	IEC 60243-1	48
Electric strength (3mmt)	kV/mm	IEC 60243-1	23
Volume resistivity	Ω·cm	IEC 60093	3 × 10 <sup>16</sup>
Volume resistivity (Our standard)	Ω·cm		-
Relative permittivity (1kHz)		IEC 60250	4.1
Relative permittivity (1MHz)		IEC 60250	3.7
Dielectric dissipation factor (1kHz)		IEC 60250	0.02
Dielectric dissipation factor (1MHz)		IEC 60250	0.03
Tracking resistance (CTI)	V	IEC 60112	175
Arc resistance	S	ASTM D495	127
Mold Shrinkage (80×80×1mmt, Flow direction, Inj. pressure 60MPa)	%	Our standard	0.01
Mold Shrinkage (80×80×1mmt, Transverse direction, Inj. pressure60MPa)	%	Our standard	0.42
Mold Shrinkage (80×80×1mmt, Flow direction, Inj. pressure79MPa)	%	Our standard	-
Mold Shrinkage (80×80×1mmt, Transverse direction, Inj pressure 79MPa)	%	Our standard	-
Rockwell hardness	M(Scale)	ISO2039-2	-
Flammability		UL94	V-0
The yellow card File No.			E106764

Item	Unit	Test Method	Standard, High flow, for SMT
			GA130
			GF Reinforced
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix -1

All figures in the table are the typical values of the material and not the minimum values of the material specifications.



## **NOTES TO USERS**

- All property values shown in this brochure are the typical values obtained under conditions prescribed by applicable standards and test methods.
- This brochure has been prepared based on our own experiences and laboratory test data, and therefore all data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.
- It is the users' responsibility to investigate patent rights, service life and potentiality of applications introduced in this brochure.
  Materials we supply are not intended for the implant applications in the medical and dental fields, and therefore are not recommended for such uses.
- For all works done properly, it is advised to refer to appropriate technical catalogs for specific material processing.
- For safe handling of materials we supply, it is advised to refer to the Safety Data Sheet "SDS" of the proper material.
- This brochure is edited based on reference literature, information and data available to us at the time of creation. The contents of this brochure are subject to change without notice upon achievement of new data.
- Please contact our office for any questions about products we supply, descriptive literatures or any description in this brochure.

 ${\tt LAPEROS} \hbox{\it @} is a registered trademark of Polyplastics Co., Ltd. in Japan and other countries. }$ 

## POLYPLASTICS CO., LTD.

JR Shinagawa East Bidg.,

18-1, Konan 2-chome, Minato-ku, Tokyo, 108-8280 Japan

Tel: +81-3-6711-8610 Fax: +81-3-6711-8618

http://www.polyplastics.com/en/